

# Vniwood N.C Glossy Varnish

## **Technical Data Sheet**

### Description

VNIWOOD Gloss is a superior quality transparent Gloss varnish for wooden surfaces based on nitrocellulose and special additives for wooden surfaces.



### Technical data

Test	Method	Result
Appearance	Visual	Gloss / Transparent
Solids by Weight	In Oven @150°C for 30 min.	37 ± 2%
Specific Gravity (gm/ml)	Specific gravity Cup	0.98 ± 0.02
Viscosity	Brookfield @Sp. 2, RPM 10	3500 CP
Gloss	Gloss meter	85°±5
Drying time	Surface dry	10-15 min.
	Complete dry	30-40 min.

#### Advantage

Excellent resistance to scratching and abrasion. Excellent Transparency. Fast drying.

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.

1



# Vniwood N.C Glossy Varnish

## **Technical Data Sheet**

#### Major Uses

interior wooden surfaces. wooden and parquet floors, furniture...etc.

Surface preparation

The surface must be clean and free from oil, grease, dirt, lime scale and any other foreign contaminants.

The sandpaper is applied in the direction of the wood fruit, and it is taken into account to wipe the dust.

Close the pores by repeated application of a sealer of MIDO products.

Processing

Dilute the varnish with %50-100 of Thinner. Applying by spray gun (1.3 - 1.4 mm) (3 - 4 bar) with 3-2 coats and flash off time between each coat is 5 minutes.

### Tools Cleaning

All tools should be cleaned with Wash Thinner.

### Shelf life

24 months in the original package, tightly closed at a temperature of  $25^{\circ}C$  and %65 R.H and away from direct sunlight and heat.

Thermotical coverage

6-8 m<sup>2</sup>/ kg per coat at 25-30 microns DFT Practical coverage varies depending on porosity of wood, DFT applied and application method.

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.