

# 9035

2K Hardener

## Technical Data Sheet

### Description

9035 Hardener is an acrylic hardener to be used with acrylic paints and varnishes. It is suitable for use in case of air drying inside stoves. It provides excellent gloss, very high weathering and chemical resistance, superior performance and fast drying. It is especially designed to offer high hardness flow and smoothness.



### Uses

Recommended to be used with high quality 2K Clearcoat 9030.

### Technical Data

Color	Transparent
Basic raw materials	Mixture of special ingredients

### Preparation of substrates

The surface must be clean and free from oil, grease, dirt and any other foreign contaminants  
 New Surface: Must be sanded and cleaned by suitable Degreaser.  
 Old or Original Surfaces: well sanded and cleaned by MIDO Cleanser.

### Technical Data

Application	By mixing Hardener with HS Clearcoat and thinner as following:		
	100 ml acrylic paint	50 ml Hardener	15 – 5 ml Thinner A1
Spray gun	HVLP spray gun 1.3 – 1.4mm, 1.8-2 bar at the nozzle		
scroll Spray gun	2 normal coats (to get opacity). Recommended total dry film thickness is 40-50 microns		

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.

**9035**

2K Hardener

## Technical Data Sheet

### Packing

For more information, please refer to the company's price list or the nearest agent.

### Storage and Shelf life

12 months in the original package, tightly closed at a temperature of 25°C and away from direct sunlight and heat

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.