

# Sofa Lacquer

Gloss varnish

## **Technical Data Sheet**

## Description

SOFA LACQUER Glossy is a superior quality transparent Gloss varnish for wooden surfaces based on nitrocellulose and special additives for wooden surfaces.

#### Uses

Finish coat for interior wooden surfaces
Finish coat for home and office furniture, doors, etc.



## Product Feature

Excellent resistance to scratching and abrasion Excellent Transparency Fast drying

### **Technical Data**

Finish	Glossy
Color	Clear
Volume solid %	37% ± 2%
Density / 25°C	Approx. 0.98 kg/Liter
Viscosity	14.000- 16.000 cp
Gloss Level / 60°degree	85 % ± 2%

### Preparation of substrates

The surface must be clean and free from oil, grease, dirt, limescale and any other foreign contaminants. The sandpaper is applied in the direction of the wood fruit, and it is taken into account to wipe the dust. Close the pores by repeated application of a sealer of MIDO products.

Exotic wood / woods rich in extractives Wood or MDF Priming with JET PU Insulators

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.



# Sofa Lacquer

Gloss varnish

## **Technical Data Sheet**

## Product Preparation / STD Application

	It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation
₹ P	Stir well before use and after adding the diluent
	50% - 100% with NC Thinner 700 or recommended NC thinner depending on method of application
	spray gun 1.4 – 1.3 mm
	2 -3 coats With an interval of at least 6 hours, light sanding is always taken into account before each face to obtain an excellent appearance 5 minutes between spray coats
	Touch Dry: 10- 15 minutes Hard Dry: 30 minutes 25°C, 50% rel. humidity

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.



# Sofa Lacquer

Gloss varnish

## **Technical Data Sheet**

## Theoretical coverage

8-6 m²/kg per coat at 30-25 microns DFT Practical coverage varies depending on porosity of wood, DFT applied and application method.

## Packing

For more information, please refer to the company's price list or the nearest agent.

## Storage and Shelf life

24 months in the original package, tightly closed at a temperature of 25  $^{\circ}$  C and away from direct sunlight and hea

## Remarks

Material has to be at room temperature (20- 25°C) before use. Equipment must be cleaned immediately after use by Thinners used for thinning can be used.

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself.